Masonry

- TMS 402
- Rational Approach
- Empirical Approach



Chilehaus, Hamburg Arch: Fritz Höger, 1924

University of Michigan, TCAUP

Structures II

weakest

Slide 1 of 28

Mortar Types

Types M, S, N, O

The follo	wing	mortar	design	ations t	took eff	fect in t	he mi	d-1950's:	
М	а	S	0	Ν	w	0	r	К	

strongest

Table 2-3. Guide to the Selection of Mortar Type*

		Mortar type		
Location	Building segment	Recommended	Alternative	
Exterior, above grade	Load-bearing walls Non-load-bearing walls Parapet walls	N O** N	S or M N or S S	
Exterior, at or below grade	Foundation walls, retaining walls, manholes, sewers, pavements, walks, and patios	Sţ	M or N†	
Interior	Load-bearing walls Non-load-bearing partitions	N O	S or M N	

*Adapted from ASTM C270. This table does not provide for specialized mortar uses, such as chimney, reinforced masonry, and acid-resistant mortars. ** Type O mortar is recommended for use where the masonry is unlikely to be frozen when saturated or unlikely to be subjected to high winds or other significant lateral loads. Type N or S mortar should be used in other cases. Masonry exposed to weather in a nominally horizontal surface is extremely vulnerable to weathering. Mortar for such masonry should be selected with due caution.

Note: For tuckpointing mortar, see "Tuckpointing," Chapter 9.



Relative Parts by Volume

mortar type	Portland cement	lime	sand
М	1	¹ 4	3 ¹ 2
S	1	¹ 2	4 ¹ 2
Ν	1	1	6
Ο	1	2	9

sum should equal 1/3 of sand volume (assuming that sand has void ratio of 1 in 3)



Masonry Strength

Masonry strength, f'm, based on unit strength, fu, and mortar type



Clay Masonry

Required Net Area C of Clay Masor	f'm For Net Area	
When Used With Type M or S Mortar	When Used With Type N Mortar	Strength of Masonry (psi)
1,700	2,100	1,000
3,350	4,150	1,500
4,950	6,200	2,000
6,600	8,250	2,500
8,250	10,300	3,000
9,900		3,500
11,500		4,000

(From Masonry Standards Joint Committee Specifications for Masonry Structures, ACI 530.1/ASCE 6/TMS 602-99)



Concrete Masonry

Required Net Area Co of Concrete Mas	f'm For Net Area	
When Used With Type M or S Mortar	When Used With Type N Mortar	Compressive Strength of Masonry (psi)
1,250	1,300	1,000
1,900	2,150	1,500
2,800	3,050	2,000
3,750	4,050	2,500
4,800	5,250	3,000

(From International Building Code 2000 and Masonry Standards Joint Committee Specifications for Masonry Structures, ACI 530.1/ASCE 6/TMS 602-99)

Constructive Properties

Property		Clay Masonry	Concrete Masonry
Unit strength		8000 psi	2000 psi
Type N morter	f'_m	2440 psi	1750 psi
Type N montai	E_m	1.70x10 ⁶ psi	1.58x10 ⁶ psi
Type Mor Smortar	f'_m	2920 psi	2000 psi
Type IN OF S HIOI Lat	E_m	2.05x10 ⁶ psi	1.80x10 ⁶ psi

Typical Values

Property	Clay Masonry	Concrete Masonry
Modulus of Elasticity, E_m	$700 f_m'$	$900f'_m$
Shear Modulus, G	$0.4E_m$	$0.4E_m$
Coefficient of Creep	$\frac{0.7 \ x 10^{-7}}{psi}$	$\frac{2.5x10^{-7}}{psi}$

University of Michigan, TCAUP

Structures II

Slide 5 of 28

Analysis and Design

Empirical approach

based on experience limits on lateral loading limits on height limits on eccentricity (basically, no flexure) non-reinforced



Rational approach

based on Strength Design (LRFD) either reinforced or non-reinforced limited by strength





Masonry Strength

Masonry strength, f'm, based on unit strength, fu, and mortar type



Clay Masonry

Required Net Area Co of Clay Masor	f'm For Net Area	
When Used With Type M or S Mortar	When Used With Type N Mortar	Strength of Masonry (psi)
1,700	2,100	1,000
3,350	4,150	1,500
4,950	6,200	2,000
6,600	8,250	2,500
8,250	10,300	3,000
9,900		3,500
11,500		4,000

(From Masonry Standards Joint Committee Specifications for Masonry Structures, ACI 530.1/ASCE 6/TMS 602-99)



Concrete Masonry

Required Net Area Co of Concrete Mas	f'm For Net Area	
When Used With When Used With Type M or S Mortar Type N Mortar		Compressive Strength of Masonry (psi)
1,250	1,300	1,000
1,900	2,150	1,500
2,800	3,050	2,000
3,750	4,050	2,500
4,800	5,250	3,000

(From International Building Code 2000 and Masonry Standards Joint Committee Specifications for Masonry Structures, ACI 530.1/ASCE 6/TMS 602-99)

Rational Masonry Analysis Procedure Strength Design – **non-reinforced**

Rational Approach

for axial compression using TMS 402 (2016)

Section Properties of Concrete Masonry Walls NCMA TEK 14 – 1B (attached to problem description, and also on Canvas, and on NCMA website)



University of Michigan, TCAUP

Structures II

Slide 9 of 28

Rational Masonry Analysis Procedure Strength Design – non-reinforced

Rational Approach

for axial compression using TMS 402 (2016)

Section Properties of Concrete Masonry Walls NCMA TEK 14 – 1B (attached to problem description and also on Canvas and on NCMA website)

	3a: H	orizontal Section	Properties (1	Masonry Sp	oanning Ver	tically)
		Grout	Mortar	Net cros	ss-sectional p	propertiesA
	Unit	spacing (in.)	bedding	A_n (in. ² /ft)	I_n (in. ⁴ /ft)	S_n (in. ³ /ft)
Α	Hollow	No grout	Face shell	30.0	308.7	81.0
В	Hollow	No grout	Full	41.5	334.0	87.6
D/I	100% sc	olid/solidly grouted	Full	91.5	443.3	116.3
С	Hollow	16	Face shell	62.0	378.6	99.3
1	Hollow	24	Face shell	51.3	355.3	93.2
	Hollow	32	Face shell	46.0	343.7	90.1
	Hollow	40	Face shell	42.8	336.7	88.3
	Hollow	48	Face shell	40.7	332.0	87.1
	Hollow	72	Face shell	37.1	324.3	85.0
T	Hollow	96	Face shell	35.3	320.4	84.0
	Hollow	120	Face shell	34.3	318.0	83.4

Table 3—8-inch (203-mm) Single Wythe Walls, 1¹/₄ in. (32 mm) Face Shells (standard)

University of Michigan, TCAUP



Rational Masonry Analysis Example Strength Design – non-reinforced

Rational Approach

for axial compression using TMS 402 (2016)

2. Find the net area, A_n, and Moment of Inertia, I_n (see NCMA TEK 14-1B)

3a: He	orizontal Section	Properties (Masonry Sp	anning Ver	tically)
	Grout	Mortar	Net cros	s-sectional p	propertiesA
Unit	spacing (in.)	bedding	A_n (in. ² /ft)	I_n (in. ⁴ /ft)	S_n (in. ³ /ft)
Hollow	No grout	Face shell	30.0	308.7	81.0
Hollow	No grout	Full	41.5	334.0	87.6
100% so	lid/solidly grouted	Full	91.5	443.3	116.3
Hollow	16	Face shell	62.0	378.6	99.3
Hollow	24	Face shell	51.3	355.3	93.2
Hollow	32	Face shell	46.0	343.7	90.1
Hollow	40	Face shell	42.8	336.7	88.3
Hollow	48	Face shell	40.7	332.0	87.1
Hollow	72	Face shell	37.1	324.3	85.0
Hollow	96	Face shell	35.3	320.4	84.0
Hollow	120	Face shell	34.3	318.0	83.4

Table 3—8-inch (203-mm) Single Wythe Walls, 1¹/₄ in. (32 mm) Face Shells (standard)

Rational Masonry Analysis Example Strength Design – non-reinforced	Rational Approach for axial compression using TMS 402 (2016)
3. Calculate $r = \sqrt{I}/A$ TEN How A	KIH-IB 8" SINGLE KLYTHE LOW BLOCK - GROUTE24"O.C FACE SHELL MORTAR = 51.3 m² In = 355.3 m ⁴ (NET)
4. Calculate ^{<i>h</i>} / _{<i>r</i>} r	$= \sqrt{\frac{1}{A}} = \sqrt{\frac{355.3}{51.3}} = 1.952 \text{ m}$ $= \frac{12'(12)}{1.952} = 73.75' < 99 \text{ i. EQ 9-11}$
5. Choose the axial strength equation, I If $h/r < 99$ use TMS 402 eq.9-11 If $h/r > 99$ use TMS 402 eq.9-12	Pn: (Equation 9-11) for h/r < 99 $P_n = 0.80 \left\{ 0.80 A_n f'_m \left[1 - \left(\frac{h}{140r}\right)^2 \right] \right\}$
University of Michigan, TCAUP Str	uctures II Slide 13 of 28
Rational Masonry Analysis Example Strength Design – non-reinforced	Rational Approach for axial compression using TMS 402 (2016)
Given: geometry: 8" block, grouted 24" o. material: f'm = 3000 psi Area An = 51.3 in²/ft height h = 12 ft r = 1.952 in	c. (Equation 9-11) for h/r < 99 $P_n = 0.80 \left\{ 0.80 A_n f'_m \left[1 - \left(\frac{h}{140r} \right)^2 \right] \right\}$
6 Calculate øPn	$P_n = 0.8 \left[0.8 A_n f'_n \left(1 - \left(\frac{n}{1 + 1} \right)^2 \right) \right]$

Pu = 1,2 (25) + 1.6 (20) = 62 K/FT

Pu = 62 %r < 64 %r = 4 Pu :. 0KV

Lateral Force Resistance

Stability requires at least 2 points of intersection.

Force is more evenly resisted with centroid of walls in the kern of slab



University of Michigan, TCAUP

Structures II

Slide 15 of 28

Empirical Approach

TMS 402-16 Tab. CC A.1.1 Checklist for use of empirical design

foundation:



COMMENTARY

Table CC-A.1.1 — Checklist for use of Appendix A – Empirical Design of Masonry

1.	Risk Category IV structures, or portions thereof, are not permitted to be designed using Appendix A.						
2.	Partitions are not permitted to be designed using Appendix A.						
3.	Use of empirical design is limited based on Seismic Design Category, as described in the following table.						
	Seismic Design Category	Participating Walls	Non-Participating Walls, except partition walls				
	A	Allowed by Appendix A	Allowed by Appendix A				
	В	Not Allowed	Allowed by Appendix A				
	С	Not Allowed	With prescriptive reinforcement per 7.4.3.1 ¹				
	D, E, and F	Not Allowed	Not Allowed				
	¹ Lap splices are required to be	¹ Lap splices are required to be designed and detailed in accordance with the requirements of Chapters 8 or 9.					
4.	Use of empirical design is limited based on wind speed at the project site, as described in Code A.1.2.3 and Code Table A.1.1.						
5.	If wind uplift on roofs result in net tension, empirical design is not permitted (A.8.3.1).						
6.	Loads used in the design of masonry must be listed on the design drawings (1.2.1b).						
7.	Details of anchorage to structural frames must be included in the design drawings (1.2.1e).						
8.	The design is required to include provisions for volume change (1.2.1h). The design drawings are required to include the locations and sizing of expansion, control, and isolation joints.						
9.	If walls are connected to structural frames, the connections and walls are required to be designed to resist the interconnecting forces and to accommodate deflections (4.4). This provision requires a lateral load and uplift analysis for exterior walls that receive wind load and are supported by or are supporting a frame or roofing system.						
10.	Masonry not laid in running bond (for example, stack bond masonry) is required to have horizontal reinforcement (4.5).						
11.	A project quality assurance plan is required (3.1) with minimum requirements given in TMS 602 Tables 3 and 4 for Quality Assurance Level 1.						
12.	The resultant of gravity loads must be determined and assured to be located within certain limitations for walls and piers (A.1.2.1).						
13.	Ensure compliance of the design with prescriptive floor, roof, and wall-to-structural framing anchorage requirements, as well as other anchorage requirements (A.8.3 and A.8.4).						
14.	Type N mortar is not permitted for foundation walls (A.6.3.1(g)).						

15. Design shear wall lengths, spacings, and orientations to meet the requirements of Code A.3.1.

University of Michigan, TCAUP

Empirical Approach	Table 1.5-1 Risk Category of Buildings and Other Structures for Flood, Wind, Snow, Earthquake, and Ice Loads				
Risk Catagories:	Use or Occupancy of Buildings and Structures	Risk Category			
ASCE – 7	Buildings and other structures that represent low human life in the event of failure	risk to I			
category IV is "not permitted"	All buildings and other structures except those liste Categories I, III, and IV	ed in Risk II			
with empirical approach	Buildings and other structures, the failure of white pose a substantial risk to human life	ch could III			
	Buildings and other structures, not included in R Category IV, with potential to cause a substantial impact and/or mass disruption of day-to-day civili the event of failure	isk economic ian life in			
	Buildings and other structures not included in Risk IV (including, but not limited to, facilities that man process, handle, store, use, or dispose of such subs hazardous fuels, hazardous chemicals, hazardous explosives) containing toxic or explosive substance the quantity of the material exceeds a threshold of established by the Authority Having Jurisdiction sufficient to pose a threat to the public if released	Category nufacture, stances as waste, or ces where quantity and is d ^a			
	Buildings and other structures designated as essen	ntial IV			
	Buildings and other structures, the failure of whi pose a substantial hazard to the community Buildings and other structures (including, but not 1 facilities that manufacture, process, handle, store, dispose of such substances as hazardous fuels, ha chemicals, or hazardous waste) containing suffici quantities of highly toxic substances where the qu the material exceeds a threshold quantity establish Authority Having Jurisdiction and is sufficient to threat to the public if released ^a	ch could imited to, use, or izzardous ent uanity of ued by the p pose a			
	Buildings and other structures required to mainta functionality of other Risk Category IV structures	in the s			
University of Michigan, TCAUP	Structures II	Slide 17 of 28			

Empirical Approach

Wind limitations:

Basic wind speed \leq 115 mph (see TMS 402-16 Tab. A.1.1)



Seismic limitations:

Can generally be used for Seismic Design Category (SDC) A, B, or C, or only A if part of the seismic lateral force resisting system.



Empirical Design of Masonry TMS 402-16

Height limits by wind speed and application

		Basic Wind Speed, mph (mps) ¹			
Element Description	Building Height, ft (m)	Less than or equal to 115 (51)	Over 115 (51) and less than or equal to-120 (54)	Over 120 (54) and less than or equal to 125 (56)	Over 125 (56)
Masonry elements that are part of the lateral-force-resisting system	35 (11) and less		Permitted		Not Permitted
	Over 180 (55)	Not Permitted			
Interior masonry loadbearing elements that are not part of the	Over 60 (18) and less than or equal to 180 (55)	Permitted Not Permitted			
lateral-force-resisting system in buildings other than enclosed as defined by ASCE 7	Over 35 (11) and less than or equal to 60 (18)	Pern	nitted	Not Pe	ermitted
1993年1月1日(1997年1月) 1999年1日(1997年1月) 1月1日日日日日日日日日日日日日日日日日日日日日日日日日日日日日日日日日	35 (11) and less	week and a serie residuated series and a series residuated a management of the series	Permitted	3 21071	Not Permitted
Lands (1997) - Al-Alas (1997) Alas (1997) - Al-Alas (1997) Alas (1997) - Alas (1997) - Alas (1997) - Alas (1997) - Alas (1997) - Alas (1997) - A	Over 180 (55)	and and the first	Not Pe	ermitted	
Exterior masonry elements that are not part of the lateral-force-resisting system	Over 60 (18) and less than or equal to 180 (55)	Permitted		Not Permitted	
	Over 35 (11) and less than or equal to 60 (18)	Pern	nitted	Not Pe	ermitted
Exterior masonry elements	35 (11) and less		Permitted		Not Permitted
Basic wind speed as given in ASCE 7		Energy Contract Contr			

Empirical Design of Masonry TEK 14-8B (also TMS 402 – Tab. A.5.1) International Building Code (IBC) Limitations:

- 1. Lateral support requirements
- 2. Location of gravity load (in middle 1/3 of wall)
- 3. Maximum unreinforced spans

Table 2—Wall Lateral Support Requirements (ref. 1)		Table 3—Maximur	n Unreinf	orced Wa	ll Spans, f	ft (m) ^A
	Maximum wall length-to	Wall thickness, in. (mr	n) 6 (152)	8 (203)	10 (254)	12 (305)
	thickness or height-to	Bearing walls				
Construction (unreinforced)	thickness ratio ^A	Solid or solid grouted	10 (3.0) ^B	13.3 (4.1)	16.6 (5.1)	20 (6.1)
Bearing walls		All other	9 (2.7) ^B	12 (3.7)	15 (4.5)	18 (5.5)
Solid units or solid grouted	20	Nonbearing walls				
All others	18	Exterior	9 (2.7)	12 (3.7)	15 (4.5)	18 (5.5)
Nonbearing walls		Interior	18 (5.5)	24 (7.3)	30 (9.1)	36 (11)
Exterior	18	Cantilever Walls ^C				
Interior	36	Solid	3 (0.9)	4 (1.2)	5 (1.5)	6 (1.8)
Cantilever walls ^B		Hollow	2 (0.6)	2.6 (0.8)	3.3 (1.0)	4 (1.2)
Solid	6	Parapets ^C	1.5 (0.5)	2 (0.6)	2.5 (0.8)	3 (0.9)
Hollow	4	A Note that Def 6 inc	Index max	lifed man	inamanta d	For walls
Parapets (8-in. (203-mm) thick min.)	в 3	with openings.	nudes mod	imea iequ	irements i	or wans
^A Ratios are determined using nomin	al dimensions. For multi-	^B Unreinforced 6-in. (1	52-mm) tl	nick bearin	g walls ar	e limited
wythe walls where wythes are bonded by masonry headers,		to one story in height	t.			
the thickness is the nominal wall thickness. When multiwythe		^C For these cases, span	s are maxi	mum wall	heights.	
walls are bonded by metal wall ties, the thickness is taken						
as the sum of the wythe thicknesses. Note that Reference 6						
includes modified requirements fo	r walls with openings.					
^B The ratios are maximum height-to not limit wall length.	o-thickness ratios and do					
University of Michigan, TCAUP	Str	uctures II			Slide 20 of	28

Masonry Strength

Masonry strength, f'm, based on unit strength, fu, and mortar type



Clay Masonry

Required Net Area C of Clay Masor	f'm For Net Area	
When Used With Type M or S Mortar	When Used With Type N Mortar	Strength of Masonry (psi)
1,700	2,100	1,000
3,350	4,150	1,500
4,950	6,200	2,000
6,600	8,250	2,500
8,250	10,300	3,000
9,900		3,500
11,500		4,000

(From Masonry Standards Joint Committee Specifications for Masonry Structures, ACI 530.1/ASCE 6/TMS 602-99)



Concrete Masonry

Required Net Area Co of Concrete Mas	f'm For Net Area		
When Used With Type M or S Mortar	When Used With Type N Mortar	Compressive Strength of Masonry (psi)	
1,250	1,300	1,000	
1,900	2,150	1,500	
2,800	3,050	2,000	
3,750	4,050	2,500	
4,800	5,250	3,000	

(From International Building Code 2000 and Masonry Standards Joint Committee Specifications for Masonry Structures, ACI 530.1/ASCE 6/TMS 602-99)

University of Michigan, TCAUP

Structures II

Slide 21 of 28

Empirical Design of Masonry TEK 14-8B (also TMS 402 – Tab. A.4.2) Allowable compressive stress of concrete masonry:

ı.

Solid or solidly grouted walls

Table 4—Allowable Compressive Stress for				
Empirical Design of Masonry				
All	owable compre	ssive stresses		
b	ased on gross ci	oss-sectional		
1994 - 1994	area, psi	(MPa) ^A		
Gross area compressive	Type M or S	Type N		
strength of unit, psi (MPa)	mortar	mortar		
Solid and Solidly Grouted M	lasonry (refs. 1	, 6):		
Solid concrete brick:				
8,000 (55) or greater	350 (2.41)	300 (2.07)		
4,500 (31)	225 (1.55)	200 (1.38)		
2,500 (17)	160 (1.10)	140 (0.97)		
1,500 (10)	115 (0.79)	100 (0.69)		
Grouted concrete masonry:				
4,500 (31) or greater	225 (1.55)	200 (1.38)		
2,500 (17)	160 (1.10)	140 (0.97)		
1,500 (10)	115 (0.79)	100 (0.69)		
Solid concrete masonry units:				
3,000 (21) or greater	225 (1.55)	200 (1.38)		
2,000 (14)	160 (1.10)	140 (0.97)		
1,200 (8.3)	115 (0.79)	100 (0.69)		
Hollow walls (noncomposite masonry bonded ^B):				
Solid units:				
2,500 (17) or greater	160 (1.10)	140 (0.97)		
1,500 (10)	115 (0.79)	100 (0.69)		
21.02		- 12 - 12		

Hollow unit walls

A	Allowable compressive stresses					
	based on gross cross-sectional					
	area, psi	(MPa) ^A				
Gross area compressive	Type M or S	Type N				
strength of unit, psi (MPa)	mortar	mortar				
Hollow Unit Masonry (Units Complying With ASTM						
C 90-06 or Later) (ref. 6) ^C :	in complying					
Hollow loadbearing CMU, t	< 8 in. (203 mm) ^D	:				
2,000 (14) or greater	140 (0.97)	120 (0.83)				
1,500 (10)	115 (0.79)	100 (0.69)				
1,000 (6.9)	75 (0.52)	70 (0.48)				
700 (4.8)	60 (0.41)	55 (0.38)				
Hollow loadbearing CMU, 8 in. $< t < 12$ in. (203 to 305 mm) ^p :						
2,000 (14) or greater	125 (0.86)	110 (0.76)				
1,500 (10)	105 (0.72)	90 (0.62)				
1,000 (6.9)	65 (0.49)	60 (0.41)				
700 (4.8)	55 (0.38)	50 (0.35)				
Hollow loadbearing CMU, $t \ge 12$ in $(305 \text{ mm})^{\text{D}}$:						
2,000 (14) or greater	115 (0.79)	100 (0.69)				
1,500 (10)	95 (0.66)	85 (0.59)				
1,000 (6.9)	60 (0.41)	55 (0.38)				
700 (4.8)	50 (0.35)	45 (0.31)				
Hollow walls (noncomposite masonry bonded ^B):						
$t \le 8 \text{ in.} (203 \text{ mm})^{D}$	75 (0.52)	70 (0.48)				
8 < t < 12 in (203 to 305 m	mm) ^D 70 (0.48)	65 (0.45)				
$t \ge 12 \text{ in } (305 \text{ m.m})^{\text{D}}$	60 (0.41)	55 (0.38)				

Empirical Concrete Masonry

Procedure using TMS 402 - 2016

Given: location, geometry, material Find: strength (load capacity)

- Check axial loading must be within middle 1/3
- 2. Check seismic category to be A, B, or C, or only A if part of the seismic lateral force resisting system.
- 3. Check wind speed (ASCE-7 2016) compare with Tab. A.1.1
- 4. Check minimum thickness. $1 \text{ story} = 6^{\circ} \text{ min.}$ $2 \text{ story} = 8^{\circ} \text{ min.}$
- 5. Check lateral support (vertical or horizontal) tables 2 and 3 TEK 14-8B or TMS 402 - Tab. A.5.1
- 6. Determine allowable compressive stress from table 4 TEK 14-8B or TMS 402 – Tab. A.4.2
- 7. Allowable load = (stress) (gross area) (not LRFD so no γ factors)

University of Michigan, TCAUP



Empirical Design Example

Given:

8" hollow non-reinforced CMU wall interior wall, Ann Arbor, Mich. DL = 150 psf

Find: LL capacity

Checks:

Axially loaded : loaded within middle 1/3 (kern)

Seismic Category: A, B, or C, or only A if part of the seismic lateral force resisting system

Wind:

less that 115 mph (ASCE 7 - 2016)





FOR ANN ARBOR : SPC > A . WIND LOAD 107 MPH < 115 V



35 (11) and less

Over 180 (55)

Over 60 (18) and

less than or equal

to 180 (55)

Over 35 (11) and

less than or equal to 60 (18)

35 (11) and less

Permitted

Permitted

Exterior masonry elements

system

Exterior masonry elements that are

not part of the lateral-force-resisting

Not Permitted

Not Permitted

Permitted

Permitted

Not Permitted

Not Permitted

Not Permitted

Empirical Design Example

Checks:

Minimum bracing - table 2

Maximum unreinforced height - table 3

MAX HEIGHT THELE 1 10'

H/t (TABLE 2)

MAX. UNREINF. HEIGHT

120" = 15 < 18 V

TABLE 3 -> 10' < 12'

12" & DL= 150 PSF

10'

Ag = 7.625 x12 = 91.57

281 ANN SPEOR

fu = 1000 psi

5 MORTAR

8"HOLLOWCHU

University of Michigan, TCAUP

Structures II

Slide 27 of 28

Empirical Design Example Find allowable stress – table 4

Find load P = F Ag

Calculate per foot using gross Area

psi (N	lpa)
Complying W	ith ASTM
Type M or S	5 Type N
3 in mortar	mortar
140 (0.97)	120 (0.83)
115 (0.79)	100 (0.69)
75 (0.52)	70 (0.48)
60 (0.41)	55 (0.38)
< t < 12 in. (203	8 to 305 mm) ^D :
125 (0.86)	110 (0.76)
105 (0.72)	90 (0.62)
65 (0.49)	60 (0.41)
55 (0.38)	50 (0.35)
12 in (305 mm)) ^D :
115 (0.79)	100 (0.69)
95 (0.66)	85 (0.59)
60 (0.41)	55 (0.38)
50 (0.35)	45 (0.31)
nasonry bonded	d ^B):
75 (0.52)	70 (0.48)
n) ^D 70 (0.48)	65 (0.45)
60 (0.41)	55 (0.38)
	psi (N Complying W Type M or S in mortar 140 (0.97) 115 (0.79) 75 (0.52) 60 (0.41) < t < 12 in. (203) 125 (0.86) 105 (0.72) 65 (0.49) 55 (0.38) 12 in (305 mm) 115 (0.79) 95 (0.66) 60 (0.41) 50 (0.35) nasonry bonder 75 (0.52) n) ^D 70 (0.48) 60 (0.41)

